



Aluminum Bronze (% Max. unless shown as range or min.)

Family	Alloy	Cu%	Sn%	Pb%	Zn%	Fe%	Sb%	Ni%	S%	P%	Al%	Mn%	Si%	Bi%	Others	
Aluminum Bronze	C95200	86.0min ^G	–	–	–	2.5-4.0	–	–	–	–	8.5-9.5	–	–	–	–	
	C95300	86.0min ^G	–	–	–	0.8-1.5	–	–	–	–	9.0-11.0	–	–	–	–	
	C95400	83.0min ^H	–	–	–	3.0-5.0	–	1.5	–	–	10.0-11.5	0.50	–	–	–	
	C95410	83.0min ^H	–	–	–	3.0-5.0	–	1.5-2.5	–	–	10.0-11.5	0.50	–	–	–	
	C95500	78.0min ^H	–	–	–	3.0-5.0	–	3.0-5.5	–	–	10.0-11.5	3.5	–	–	–	
	C95520	74.5min ^{S,H}	0.25	0.03	0.30	4.0-5.5	–	4.2-6.0	–	–	10.5-11.5	1.5	0.150	–	–	
	C95600	88.0min ^G	–	–	–	–	–	0.25	–	–	6.0-8.0	–	1.8-3.2	–	–	
	C95700	71.0min ^H	–	0.03	–	–	2.0-4.0	–	1.5-3.0	–	–	7.0-8.5	11.0-14.0	0.10	–	–
	C95800	79.0min ^H	–	0.02	–	–	3.5-4.5T	–	4.0-5.0T	–	–	8.5-9.5	0.8-1.5	0.05	–	–
	C95900	Remainder ^H	–	–	–	–	3.0-5.0	–	0.50	–	–	12.0-13.5	1.50	–	–	–

© The Federal Metal Company • 7250 Division Street • Bedford, Ohio 44146 • United States • Contact 800.736.6636 or visit us at: www.federalmetal.com

^G Total named elements = 99.0% min.

^H Total named elements = 99.5% min.

^S Cr will be 0.05 max and Co 0.20 max.

^T Ni > Fe