



Cupro Nickel and Monel (% Max. unless shown as range or min.)

Family	Alloy	Cu%	Sn%	Pb%	Zn%	Fe%	Sb%	Ni%	S%	P%	Al%	Mn%	Si%	Bi%	Others	C	Mg	Nb
Cupro Nickel and Monel	C96200	84.5-87.0 ^H	–	0.005	–	1.0-1.8	–	9.0-11.0	0.02	0.02	0.005	0.8-1.5	0.25	–	–	0.05	–	1.0
	C96400	65.0-67.0 ^H	–	0.005	–	0.25-1.0	–	29.5-31.5	0.02	0.02	0.005	0.8-1.5	0.30-0.50	–	–	0.05	–	0.5-1.5
	M-35-1 ^A	26.0-33.0	–	–	–	3.50	–	Balance	0.03	0.03	–	1.5	1.25	–	–	0.35	–	0.5
	M-35-2	26.0-33.0	–	–	–	3.50	–	Balance	0.03	0.03	–	1.5	2.00	–	–	0.35	–	0.5
	M-30H	27.0-33.0	–	–	–	3.50	–	Balance	0.03	0.03	–	1.5	2.7-3.7	–	–	0.30	–	–
	M-25S	27.0-33.0	–	–	–	3.50	–	Balance	0.03	0.03	–	1.5	3.5-4.5	–	–	0.25	–	1.0-3.0
	M-30C ^A	26.0-33.0	–	–	–	3.50	–	Balance	0.03	0.03	–	1.5	1.0-2.0	–	–	0.30	–	–

© The Federal Metal Company • 7250 Division Street • Bedford, Ohio 44146 • United States • Contact 800.736.6636 or visit us at: www.federalmetal.com

^A Best application; M-35-1 or M-30C when weldability is required

^H Total named elements = 99.5 % min.